

GWPB



Welding/Gas - 20 bar - orange - ISO 3821 (EN 559)

Application:

A flexible hose for transporting liquid gas (LPG), for CNG, methylacetylene and propandiene mixes (MPS).

For welding and cutting.

Standard/approval:

ISO 3821:2008 (formerly EN 559:2003).

Notice:

BS 3212-2:1991 available on request.

Temperature range:

-30°C / +70°C.

Safety factor:

3:1

Tube:

NBR, black, smooth.

Reinforcement:

Textile spiral.

Cover:

EPDM, orange, smooth.

Marking:

continuous inkjet, black letters:

"SEMPERIT (S) GWPB ISO 3821 (EN559) PN 2MPa (20 bar) DN -30°C year MADE IN EU".



Article number	Internal-Ø in		Wall width	External-Ø	Work. pressure	Number of inserts	Bending radius	Weight approx.	Coil length
	mm	Acetylene inch	in mm	in mm	(max.) bar		(min.) in mm	kg/m	(max.) m
68404 0435	4,0		3,5	11,0	20	2	40	0,12	50
68404 0535	5,0	3/16	3,5	12,0	20	2	40	0,13	50
68404 0630	6,3		3,0	12,3	20	2	40	0,11	50
68404 0635	6,3	1/4	3,5	13,3	20	2	40	0,14	50
68404 0830	8,0		3,0	14,0	20	2	40	0,13	50
68404 0835	8,0	5/16	3,5	15,0	20	2	40	0,18	50
68404 0930	9,0		3,0	15,0	20	2	45	0,15	50
68404 0935	9,0		3,5	16,0	20	2	45	0,20	50
68404 1035	10,0	3/8	3,5	17,0	20	2	50	0,21	50
68404 1250	12,5	1/2	5,0	22,5	20	2	65	0,36	50

Please note: Before using our products with new or untested media, or for applications that are not clearly indicated in the product information, written advice must be obtained from a specialist dealer or a Semperit application engineer. For safety reasons, all products must be inspected regularly for operational safety and replaced in the event of any damage (especially of the cover) or unusual signs of wear and tear. All products must be stored, handled and maintained in accordance with all our respective instructions and DIN 7716:1982. The information in our catalogue as well as each individual datasheet is subject to change at any time without notice since we are constantly developing and improving our products and due to constant technical developments after the latest release date of the catalogue and/or individual datasheets. In order to always have the latest product and safety information make sure you visit our website (www.semperflex.com) regularly or contact one of our specialist dealers or a Semperit application engineer. All contracts with Semperflex are exclusively subject to our general terms and conditions (available at www.semperfitgroup.com). Additional important general information about the range, choice and safe use of our products can be found at our website (www.semperflex.com) and must be followed without exception.

Important notice: Our catalogue and any individual datasheet have been prepared with great care in order to provide you with all the information you need. The information contained therein is based on the latest state-of-the-art industrial technology and many years of experience and testing; whenever indicated for a certain product, we also confirm conformity with the resistance requirements of the media listed in ISO TR 7620:2005(E). However, the individual conditions of storage, maintenance and use decisively affect the safe and durable use of each product. The quality and safety of our products as indicated in the catalogue or individual datasheets are therefore strictly subject to the continuous observance of all specifications and restrictions in our written product information and applicable laws and standards, the specifications regarding resistance to chemicals and our cleaning procedures. We reject any liability for setty issues or other consequences due to improper product choice, maintenance or handling (e.g. squashing, rupturing, stretching or filling with non-approved media). Our products must not be used in airplanes or other aerial vehicles under any circumstance. Unless specified otherwise, all hoses are manufactured according to EN ISO 1307:2008.

